

**AISI Thickness Tolerance Ranges
Galvanized Steel Sheets**

Gage No.	Thickness. inches		lbs. per sq.ft.	Gage No.	Thickness. inches		lbs. per sq.ft.
	Dec. Equiv.	Tol. Rnge.	Weight Equiv.		Dec. Equiv.	Tol. Rnge.	Weight Equiv.
10	.1382	.1472 .1292	5.78125	21	.0366	.0406 .0326	1.53125
11	.1233	.1323 .1143	5.15625	22	.0336	.0376 .0296	1.40625
12	.1084	.1174 .0994	4.53125	23	.0306	.0346 .0266	1.28125
13	.0934	.1014 .0854	3.90625	24	.0276	.0316 .0236	1.15625
14	.0785	.0865 .0705	3.28125	25	.0247	.0287 .0207	1.03125
15	.0710	.0770 .0650	2.96875	26	.0217	.0247 .0187	.90625
16	.0635	.0695 .0575	2.65625	27	.0202	.0232 .0172	.84375
17	.0575	.0625 .0525	2.40625	28	.0187	.0217 .0157	.78125
18	.0516	.0566 .0466	2.15625	29	.0172	.0202 .0142	.71875
19	.0456	.0506 .0406	1.90625	30	.0157	.0187 .0127	.65625
20	.0396	.0436 .0356	1.95625				

Weight equivalents based on density of .2904 lb. per cubic inch
Gages 10, 11, 12 – tolerances shown are for widths over 40” to 60” inclusive
All other gages – tolerances shown are for widths over 32” to 60” inclusive